



UNITED # STAGCG-95 (HARD STERLING SILVER CASTING GRAIN)

UNITED # STAGCG-95 is a proprietary hard De-oxidized Sterling Silver Grain designed to achieve maximum hardness and porosity. Sterling # STAGCG-95 has been developed to have hardness approximately equal to standard sterling silver, while still retaining the advantageous characteristics of our other sterling silver grains.

Melting : Traditional methods of melting regular sterling silver I.E. (as cool as possible) will cause a variety of problems. Most failures with these sterling products are caused by too low of a melt temperature. Customers familiar with silicon deoxidized gold casting alloys should have less trouble adjusting to the appearance of these silvers.

-
- Casting Temperature** : 1,020 - 1,040°C / 1,868-1904°F
- Flask Temperature** : Use your regular flask temperatures in the range of 1100 F to 1250 F depending on the size of flask and type of jewelry being cast.
- Quench Time** : 15 - 20 minutes.
- Specific Gravity** : 10.28
- Remelting** : We recommend a 50% fresh mix.
- Investment Removal** : Most standard investment removers will successfully remove the investment powder. The best solutions are the sulfuric and hydrofluoric based products.
- Fluxing** : It maybe necessary to flux these silver melts. We recommend Boric acid.
Do not use Carbon Containing Fluxes or Charcoal. Skim any surface oxides off the surface before stirring.
- Hardness and** : This silver as cast will have a hardness similar to traditional sterling silver.
- Heat Treatment** : It can be hardened further by heat treatment at 300°C/ 575°F for 2 hr., and air cool.
- Soldering** : Over-heating while soldering is to be avoided.
United # SSA is a silver solder alloy or ready to use Easy-Medium-Hard silver solder.
- Notes** : Melt temperature may vary with type of unit.

Representative Office :

UNITED PM (THAILAND) CO., LTD. 427/15-16 Krungthonburi Rd., Klongtongsai, Klongsan, Bangkok. 10600, Thailand.

Tel : (662) 4400643, 4400673 Fax : (662) 8622344 Mobile 081- 6948866, 081-7517384 E-mail : sales@unitedpmthailand.com