



UNITED ALLOY # PD-2

Be insured in quality, Be insured in service, Be insured in “United Alloys.

UNITED ALLOY is uniquely different from other available alloys. Combining the highest purity metals available, stringent quality control, special de-oxidizers and grain refiners, produce trouble-free, superior quality castings and fabrication or rolling (hand-made).

UNITED ALLOY # PD-2 is designed for 14K - 18K Palladium White Gold, which produces a Vanilla White Color which should be Rhodium plated for optimum color. This alloy is making tremendous strides in the development of a high fluidity palladium white gold alloy which contains Technical Metals as De-oxidizers which resist oxygen absorption in melting process and better solidification characteristics to reduce the porosity which improve the quality of casting and provide high luster in finished color and can be used in normal investment equipment as Regular Casting.

We do recommend pre-graining all alloy and fine gold before casting to assure a uniform mixture.

- 1.) Melt Temperature for Alloying : 1,200 - 1,230 °C
- 2.) Melt Temperature for Casting : 1,150 - 1,250 °C
- 3.) Flask Temperature :

KARAT	WEIGHT	CENTRIFUGAL CAST	VACUUM CAST
14K - 18K	Light	650 - 700 °C	680 - 720 °C
	Medium	620 - 650 °C	650 - 680 °C
	Heavy	600 - 620 °C	620 - 650 °C

- 4.) Quench Time : After casting, wait 15 - 20 minutes before quenching flask.
- 5.) Pickling : United's Brite-Cast™ (Ammonium Bi-fluoride), Sparex # 2 (sodium bisulfate), 10% - 20% Sulfuric Acid.
 Rubber gloves and safety glasses are recommended when using acid pickle.
- 6.) Re-using : New alloy and fine gold 70%, Old gold 30%, Cleans Old gold well before re-melting.
- 7.) Specific Gravity : 14K - 14.17, 18K - 15.86
- 8.) Soldering : United Palladium White Gold Solder # 14KWHPD, # 18KWHPD.
 Laser welding is recommendation for matching white color.
- 9.) Notes : Melt temperature may vary with type of unit.

Representative Office : UNITED PM (THAILAND) CO., LTD.

467/7 2nd Floor, Mahatun Rama 3 Center, Rama 3 Road, Bang Khlo, Bang Kho Leam, Bangkok. 10120, Thailand.

Tel : (662) 292 1992, 292 1993 Fax : (662) 292 1994 Mobile 081-751 7384 E-mail : sales@unitedpmthailand.com